



GEO-LINK | 吉尔林克
STANDARDIZE AND CUSTOMIZE

G-[®]Tex PET Woven Geotextile

Geo-Link G-[®]Tex WN150 is manufactured from high tenacity polyester (PET) yarns and designed for landfill liner reinforcement, embankment over soft soil, reinforced soil slope.

Properties	(Standard)	Unit	WN
			150
Tensile Strength@Ultimate(MD/CD)[ASTM D4595]		kN	150
Elongation@Ultimate(MD)[ASTM D4595]		%	≤10±2
Puncture Resistance[ASTM D6241]		N	8500
Permittivity[ASTM D4491]		l/s	0.7
Apparent Opening Size[ASTM D4751]		mm	≤0.5
Factory Seam Strength[ASTM D4884]		kN/m	71
Thickness		mm	0.9mm
Roll Width		m	5.2
Roll Length		m	50
Color		-	White

Note:

1.MD: Machine direction, CD: Cross- Machine direction.

2. The technical data are according to our laboratories and testing institution.

Above values are on an average basis, the data was obtained from in-house test laboratory. Geo-Link keeps the right of data changes and the final explanation right. Liability Exclusion: This publication should not be construed as engineering advice. While information contained here is accurate to the best of our knowledge, Geo-Link does not warrant its accuracy or completeness. The only warranty made by Geo-Link for its products is set forth in our Product Test Report accompanies our shipment of the products, or such other written warranty as may be agreed by Geo-Link and customer. Geo-Link specifically disclaims all other warranties express or implied, including without agreed by Geo-Link and customer. Geo-Link specifically disclaims all other warranties, express or implied, including without limitation, warranties of merchantability or fitness for a particular purpose, or rising from provision of samples, a course of dealing or usage of trade.

Dalian Geo-Link Geosynthetics Co.,Ltd.

Add: No.8888-1 Southeast Industrial Zone, Youjia,Ganjingzi District, Dalian, China
P.C.: 116039

Tel: +86-(0)411 6600 7883

Fax: +86-(0)411 6600 7882

Web: www.geo-textile.com

Email: info@geo-textile.com

