


G-Meb LLD Range Geomembrane

Technical Data Sheet

GEO-LINK LLD Dec. 11th, 2009

G-Meb LLD are produced from prime linear low molecular weight (LLDPE) resins resulting in a high quality premium grade geomembrane with superior flexibility. Geo-Link LLD has been formulated to be chemical resistant, free of leachable additives and resistant to ultraviolet degradation. Our LLD are two or three layer co-extruded



(E.M.B.: Every material batch)

Property	Test Method	Frequency	Minimum Value					
Product Code			LLD050	LLD075	LLD100	LLD150	LLD20	LLD250
Thickness, (minimum average) mm	ASTM D 5199	Every roll	0.50	0.75	1.00	1.50	2.00	2.50
Lowest individual reading (-10%)			0.45	0.69	0.91	1.40	1.80	2.25
Density, g/cc	ASTM D 1505	90,000Kgs	0.94	0.94	0.94	0.94	0.94	0.94
Tensile Properties (each direction)	ASTM D 6693 , TypeIV	9,000Kgs						
Strength at Break, N/mm	Dumbell , 2ipm		13	20	27	40	53	66
Elongation at Break, %	G.L. 2.0 in (51mm)		800	800	800	800	800	800
2% Modulus (max) N/mm	ASTM D 5323	E.M.B	210	370	420	630	840	1050
Tear Resistance, N	ASTM D 1004	20,000Kgs	50	71	98	147	200	250
Puncture Resistance, N	ASTM D 4833	20,000Kgs	120	190	250	370	500	620
Axi-Symmetric Break Resistance Strain %	ASTM D 5617		30	30	30	30	30	30
Carbon Black Content, %	ASTMD 1603*/4218	9,000Kgs	2	2	2	2	2	2
Carbon Black Dispersion	ASTM D 5596	20,000Kgs	+Note1	+Note1	+Note1	+Note1	+Note1	+Note1
Oxidative Induction Time ,min	ASTMD 3895, 200 °C , 1 atm	90,000Kgs	100	100	100	100	100	100
Oven Aging at 85°C	ASTM D 5721							
Standard OIT, retained after 90 days, %	ASTM D 3895	E.M.B	35	35	35	35	35	35
UV Resistance High Pressure	ASTM D 5885							
OIT, retained after 1600 hours (min.avg), %		E.M.B	35	35	35	35	35	35
Roll Length		meters	205	135	210	140	100	80
Roll Width		meters	7	7	7	7	7	7
Approx Load Q'ty per 40' HQ		Sq.m	51660	34020	26460	17640	12600	10080

1. Machine direction (MD) and cross machine direction (XMD) average values should be on the basis of 5 test specimens each direction. -Elongation at break is calculated using a gage length of 50mm at 50mm/min. 2. The condition of the test should be 20 hour UV cycle at 75°C followed by 4 hour condensation at 60°C. 3. UV resistance is based upon percent retained values regardless of the original HP-OIT value.

+Note1: Dispersion only applies to near spherical agglomerates. 9 of 10 views shall be Category 1 or 2. No more than 1 view from Category 3.

Dalian Geo-Link Geosynthetics Co., Ltd.

Add: No.8888-1 Southeast Industrial Zone, Youjia, Ganjingzi District, Dalian, China P.C.: 116039

Tel: +86-(0)411 6600 7885

Fax: +86-(0)411 6600 7882

WebSite: www.geo-textile.com

E-Mail: info@geo-textile.com

